

ROCKWOOL AFB® is a lightweight, acoustical fire batt stone wool insulation specifically designed for steel stud and wood stud interior wall and floor applications. Its superior sound absorbency and fire protection contribute to the overall comfort and safety of occupants.

It provides increased density that reduces sound transmission. Greater noise control is further achieved when AFB® is part of the wall assembly along with gypsum boards and resilient channels.

AFB® is non-combustible and will not develop toxic smoke or promote flame spread, even when directly exposed to fire. This helps to provide valuable extra time for people to reach safety and for fire services personnel to control the spread. It is a key component of fire-rated partitions.

AFB® comes in a number of thicknesses to meet the requirements of both retrofit and new construction applications.

Learn more at rockwool.com

Quiet Spaces

The higher density of ROCKWOOL AFB® can reduce sound transmission, helping to create a quiet and comfortable space.







ROCKWOOL AFB® is a mineral wool batt insulation for interior partitions in commercial constructions where superior fire resistance and acoustical performance are required.

	Performance	Test Standard
Compliance	Mineral Fiber Thermal Insulation for Buildings, Type 1 Compliant Mineral Fiber Blanket Thermal Insulation, Type 1 Compliant Mineral Fiber Blanket Thermal Insulation, Type 7 Compliant MEA Approval, New York City Approval City of Los Angeles Approval	CAN/ULC S702 ASTM C665 ASTM C553 338-97-M RR 25444
Reaction to Fire	Flame spread index = 0; Smoke developed index = 0 Flame spread index = 0; Smoke developed index = 0 Determination of Non-combustibility of Building Materials - Non-combustible Behavior of materials at 750°C - Non-combustible Smolder Resistance - 0.09%	ASTM E84 (UL 723) CAN/ULC S102 CAN/ULC S114 ASTM E136 CAN/ULC S129
Nominal Density	> 2.5 lbs/ft³ (>40 kg/m³)†	ASTM C303
Corrosion Resistance	Stress Corrosion Cracking Tendency of Austenitic Stainless Steel - Passed Corrosion of Steel - Passed	ASTM C795 ASTM C665
Air Erosion	Maximum Air Velocity - 1000 fpm (5.08 m/s)	UL 181
Thickness Dimensions	1" through 4" (25.4 mm - 101.6 mm) in 1/2" increments as well as 5" (127 mm) and 6" (152.4 mm), 15.25" \times 47" (387 mm \times 1194 mm), 16" \times 48" (413 mm \times 1219 mm), 19.2" \times 47" (470 mm \times 1194 m 23" \times 47" (584 mm \times 1194 mm), 24" \times 48" (610 mm \times 1219 mm)	m),
Acoustical Performance	Thickness 125 Hz 250 Hz 500 Hz 1000 Hz 2000Hz 4000 Hz NRC 1.0" 0.14 0.25 0.65 0.9 1.01 1.01 0.7 1.5" 0.18 0.44 0.94 1.04 1.02 1.03 0.85 2" 0.28 0.6 1.09 1.09 1.05 1.07 0.95 3" 0.52 0.96 1.18 1.07 1.05 1.05 1.05 4" 0.86 1.11 1.2 1.07 1.08 1.07 1.1 6" 1.11 1.28 1.15 1.06 1.03 1.01 1.15	ASTM C423
Fire Rated Designs	ULC Classification Code: BZJZC UL Classification Code: BZJZ	









Issued 08-01-20 Supersedes 08-23-17 NOTE: *Master Format 1995 Edition **Master Format 2004 Edition. As ROCKWOOL has no control over installation design and workmanship, accessory materials or application conditions, ROCKWOOL does not warranty the performance or results of any installation containing ROCKWOOL's products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty is in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose.

¹Density will change with thickness. Density is not a performance criteria but is commonly referred to when specifying insulation. Actual density is the true density of the insulation and Nominal density is the effective density of the insulation relative to a historic benchmark where the insulation contained 40% non-fibrous content also known as Shot (ASTM C612-99). Please contact ROCKWOOL for more information.

